## **MARMOTILE**



# **SECTION 1: Identification of the substance/mixture and of the company/undertaking**

## 1.1 Product identifier: MARMOTILE

Manufacturer / Importer / Supplier:

#### **ANAV INDUSTRIES**

Address: Khewat No. 1358/1151, Khatoni No. 1461, Main NH-9, Near Toll Plaza, Village Rohad, Distt. Jhajjar, Haryana-124501

## Marketed By:

Marmo Solutions Pvt. Ltd.

Office Address:

WHS.1/18, 2nd floor, Kirti Nagar, Near Richi Rich Banquet Hall,

New Delhi-110015

Tel. No: 011-40586081

Emergency No: 91-9555155080 www.marmosolutions.com info@marmosolutions.com

#### 2. Marmotile:

Marmotile is adhesive for fixing ceramic tiles indoor.

#### **Characteristics:**

- Used as an adhesive for floors.
- Thickness upto 10 mm
- Prolonged workability
- Adjustable
- No sag
- Very low VOC

## 3. Specification:

- Category: Inorganic Mineral products.
- Class: Mineral adhesives for ceramic tiles and natural stone.







## **MARMOTILE**



• Rating: Tile 4

(Natural mineral content 79% ;  $CO_2$  /kg emission 145 g ; very low VOC emissions ; can be recycled as inert materials.

• This is green building rating which is dependable and reliable evaluation method for measuring and improving the environmental performance f building materials.

## 4. Notes:

- -Formulated with locally-sourced minerals meaning lower greenhouse gas emissions during transport.
- Single-component; avoiding the use of plastic cans reduces CO<sub>2</sub> emissions and the need t dispose of special waste
- Can be recycled as mineral inert material, avoiding waste disposal costs and environmental impact.

# 5. Application:

## 1.Surface:

- Cement-based screeds and mortars
- Cement-based plasters/renders

#### 2. Material on which chemical can be used:

- ceramic tiles
- Terracotta
- Ceramic mosaic
- Cement Blocks



## **MARMOTILE**



## 3.Usage:

- Flooring
- For internal use
- COMMERCIAL applications
- STREET Furniture

#### 6. PREPARATION OF THE SURFACE:

All surfaces must be dimensionally stable according to IS 1443-1972, level, cured, undamaged, compact, rigid, resistant, dry and free from any debonding agents and from damp rising. It is good practice to dampen highly absorbent concrete surfaces or apply a coat of Marmo Prime.

#### 7. ADHESIVE PREPARATION:

4.5 to 5 litres of clean water per 20 kg bag 11.25 - 12.5 litres of clean water per 50 kg bag

# 8. Application:

- To guarantee maximum adhesion it is necessary to apply a sufficient layer of adhesive.
- Large, rectangular sizes with sides > 30 cm may require adhesive to be applied directly on the back surface of the tile.
- Check samples to make sure the adhesive has been transferred to the back of the material.

## 9. Preparing the mix:

- Mix Marmotile with clean water until a smooth, lump-free paste is obtained.
- Leave to rest approximately 5 minutes and re-stir.
- •In a clean mixing container pour in 4.5 5 litres of clean water, and then add 20 kg bag/ 11.25-12.5 litres of clean water for 50 kg bag of Marmotile powder, using an electric mix (approx 300RPM) mix until a smooth, lumpfree paste is obtained. Leave the mix to rest for approximately 5 minutes and then re-stir.
- Mixed this way, Marmotile has a pot life of approximately 8 hours.



## **MARMOTILE**



## **Create elastic expansion joints:**

- •≈ 10 m2 in external applications,
- •≈ 25 m2 in internal applications,
- Every 8 metres in long, narrow applications.

Respect all structural, fractionizing, and perimeter joints present in the surfaces.

## **Product Identity**

Type: Powder

Colour: Grey, white

Bulk density (kg/m³) 1300

Dry Solids content (%): 100

COMPOSITION AND PROPERTIES OF MIXTURE (at +23°C and 50% R.H.)

Mixing ratio: 4.5 - 5 litres of clean water per 20 kg bag

11.25 - 12.5 litres of clean water per 50 kg bag

Consistency of mix: Pasty

Density of the mix (kg/m³): 1300 pH of mix: 13

Pot life: over 8 hours

Application temperature: From +5°C to +40°C

Open time (according to EN 1346) 30 minutes

Adjustability time: approx 45 minutes

Ready for grouting on walls: After 4-8 hours
Ready for grouting on floors: After 24 hours

Set to light foot traffic: 24 hours
Ready for use: 14 days



## **MARMOTILE**



#### **10. FINAL PERFORMANCES:**

Tensile adhesion strength in compliance with EN 1348 (N/mm²):

• Initial tensile adhesion strength >0.5

(after 28 days):

• Tensile adhesion strength after heat >0.5

ageing:

• tensile adhesion strength after water >0.5

immersion:

• tensile adhesion strength after >0.5

freeze/thaw cycles:

Resistance to alkalis: Excellent

Resistance to oils: Excellent (poor to vegetable oils)

Resistance to solvents: Excellent

Temperature when in use: From -30°C to +90°C

#### 11. CONSUMPTION:

Coverage per mm of thickness ≈ 1.2 kg/m<sup>2</sup>

#### 12. PACKAGING:

Marmotile is available in 20 kg bag and 50 kg bag.

#### 13. STORAGE:

When stored in dry conditions in the original, unopened bags, Marmotile has a shelf life of 12 months. If stored at high temperature and or high humidity conditions the shelf life may be reduced.

**SET TO LIGHT FOOT TRAFFIC:** Floors are set to light foot traffic after approx. 24 hours. **READY FOR USE**: Surfaces are ready for use after approx. 14 days. Swimming pools and basins can be filled after 21 days.

**Cleaning:** Tools and containers should be cleaned with plenty of water while Marmo Tile is still fresh. Surfaces should be cleaned with a damp cloth, before the adhesive dries.

#### **14. Notes:**

-Marble, natural stones and recomposed materials in general may have characteristics that vary even with reference to materials of the same chemical and physical nature



## **MARMOTILE**



#### **15. WARNING:**

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product. Please refer to the current version of the Technical Data Sheet, available from our website www.marmosolutions.com



